

Data Sheet

PLASTSTATIC 25 PE

Application: Internal antistatic for polyolefin; it gives almost instantaneous antistatic performance. However in a lot of cases the effect might be only temporarily.
Applicable for PE; PP

Active Ingredients: glycerol ester

Active Content: 25%

Carrier: Modified polyethylene

Physiology: EEC No limitations for all polymers

USA No limitations for all polymers

Supplied as: whitish granules

Dosage:

Polyolefin films: < 50 µm 0,6 - 1,0 %
> 50 µm 1,0 - 2,0 %

Polyolefin moulded articles: 2,0 - 4,0 %

Storage: It is recommended to store the PLASTSTATIC 25-PE preferably below 30°C

The information given in this data sheet is based on many years of practical experience. Nevertheless can it only be a recommendation and a basis for practical testing, where the optimum dosage has to be determined individually.

All information given herein is only a recommendation. Its use shall remain the sole responsibility of the customer. No patent guarantee whatsoever shall be implied.