

Data Sheet

PLASTRON GMS 50

Application: Internal Antistatikum for polyolefin's, it gives almost instantaneous antistatic performance. However in a lot of cases the effect might be only temporarily.

Cell stabilizing additive for expandable PE (EPE), reduces the cell shrinking.

Active Ingredients: Highly concentrated glycerol monostearate with a minimum content of 90%;

Active Content: 50 %

Carrier: Modified polyethylene

Physiology: EEC No limitations for all polymers

USA No limitations for all polymers

Supplied as: whitish granules

Dosage:

Cell stabilizing: 2,5 - 3,5 %

Polyolefin films: depending on the film thickness 0,3 - 1,0 %

Polyolefin moulded articles: 0,5 - 2,0 %

Storage: It is recommended to store the PLASTRON GMS 50 preferably below 30°C

The information given in this data sheet is based on many years of practical experience. Nevertheless can it only be a recommendation and a basis for practical testing, where the optimum dosage has to be determined individually. All information given herein is only a recommendation. Its use shall remain the sole responsibility of the customer. No patent guarantee whatsoever shall be implied.