

Data Sheet

PLASTCURE 20 DICP

Application: Organic peroxide for cross linking of PE; EPDM; EPM; SBR; EVA and rubber

Active Ingredients: Dicumyl peroxide

Active Content: 20 %

Carrier: Polyethylene

Supplied as: cylindrical granules

Technical Data:

<i>Crosslink times:</i>	150°C	65 minutes	160°C	25 minutes
	170°C	10 minutes	180°C	4 minutes

Processing Temp.: depending on the needed reaction time

Dosage:

PE	2.5 – 6.2 %	SBR	3.3 – 6.8 %
EVA	4.5 – 8.2 %	NR	4.0 – 7.5 %
EPM, EPDM	5.6 - 17 %	BR	0.7 – 3.8 %

The information given in this data sheet is based on many years of practical experience. Nevertheless can it only be a recommendation and a basis for practical testing, where the optimum dosage has to be determined individually.

All information given herein is only a recommendation. Its use shall remain the sole responsibility of the customer. No patent guarantee whatsoever shall be implied.